

## **TECHNICAL DATA**

# Fluo 300SM

A unique emulsion grade PTFE grade consisting of aggregated sub-micron PTFE spheres ideal for thin film coatings and gloss retention

### **Features and Benefits**

- PTFE clusters can be media milled into individual nanospheres less than 200 nm
- Superior gloss retention
- Provides lubricity, rub and abrasion resistance and heat resistance
- High surface area of dispersed particles allow lower dosages
- Specific surface area BET 7-10 m<sup>2</sup>/g
- Conforms to (EU) 2019/1021 & Stockholm Convention (POP)

#### Composition

Polytetrafluoroethylene (PTFE)

## **Recommended Addition Levels**

0.5-1.0% (on total formula weight)

#### **Systems and Applications**

Solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings; floor coatings.

## **Typical Properties\***

	Fluo 300SM
Melting Point °C	>316
Density @ 25 °C (g/cc)	2.20
Maximum Particle Size (µm)	22.00
Mean Particle Size (µm)	2.0 - 4.0
Primary Particle Size (nm)	200 - 250

This product is also available as a water based wax dispersion - Microspersion 300SM-50

Apr-25

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

The above data reflects typical properties. Please contact Micro Powders for official product specifications. The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.