

TECHNICAL DATA

Fluo 500

Micronized high quality virgin PTFE that provides superior lubricity, abrasion and temperature resistance to industrial coatings and inks

Features and Benefits

- Provides maximum abrasion and rub resistance
- Adds slip, lubricity and block resistance
- Imparts heat resistance
- Will not yellow in high temperature baking applications
- Conforms to (EU) 2019/1021 & Stockholm Convention (POP)

Composition

Polytetrafluoroethylene (PTFE)

Recommended Addition Levels

0.5-2.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings; seed coatings.

Typical Properties*

	Fluo 500
Melting Point °C	>316
Density @ 25 $^{\circ}$ C (g/cc)	2.20
Maximum Particle Size (μ m)	22.00
Mean Particle Size (µm)	3.0 - 5.0

PTFE (PFAS) free alternatives: PolyGlide 1226XF, Superslip 6515AL

Apr-25

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

The above data reflects typical properties. Please contact Micro Powders for official product specifications. The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.