TECHNICAL DATA



Micromide 520

Micronized fatty amide wax for maximum surface slip, scratch resistance and release properties

Features and Benefits

- Adds slip, release and lubricity with an excellent surface "feel"
- High melting point to improve heat and block resistance
- Lowers COF
- Reduces dust buildup on sanding belts and increases longevity in sanding sealers

Composition

Ethylene bis(stearamide) wax (EBS)

Renewable Carbon Index

>90%

Recommended Addition Levels

0.5-3.0% (on total formula weight)

Systems and Applications

Solvent based and energy curable coatings and inks. Wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; powdered metals.

Typical Properties*

	Micromide 520	Micromide 520XF
Melting Point $^\circ$ C	141 - 146	141 - 146
Density @ 25 $^{\circ}$ C (g/cc)	0.97	0.97
NPIRI Grind	1.5 - 3.0	1.0 - 2.0
Maximum Particle Size (μm)	22.00	15.56
Mean Particle Size (µm)	5.0 - 8.0	3.0 - 5.0

This product is also available as a water based wax dispersion - Microspersion 520

Apr-25

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

The above data reflects typical properties. Please contact Micro Powders for official product specifications. The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.