#### **TECHNICAL DATA**



# Microspersion<sup>®</sup> 300SM-50

A nonionic water based dispersion of spherical submicron PTFE

# **Features and Benefits**

- Convenient, ready-to-use, pourable nonionic wax dispersion that adds lubricity, rub and abrasion resistance
- Fluo 300SM PTFE aggregates are pre-dispersed into submicron nanoparticles
- Submicron wax particle size provides superior gloss retention
- High surface area of dispersed nanoparticles allow lower dosages
- Conforms to (EU) 2017/1000
- NOTE: This submicron wax dispersion is not freezethaw recoverable

#### **Dry Wax ID**

Fluo 300SM

# **Recommended Addition Levels**

1.0-3.0% (on total formula weight)

# **Systems and Applications**

Water based coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; printing inks and OPV's (including flexo and gravure); interior and exterior can and container coatings; coil coatings; floor coatings.

# **Typical Properties\***

	Microspersion 300SM-50
Wax Solids	50%
Viscosity @ 25 $^{\circ}$ C (cP)	2,000 - 9,000
pН	8.0 - 10.5
Density @ 25 ° C (g/cc)	1.37
Wax Mean Particle Size (µm)	< 1.0

Apr-25

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

The above data reflects typical properties. Please contact Micro Powders for official product specifications. The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.