

Microspersion® 523

A nonionic water based dispersion of a unique extra fine composite of polyethylene and PTFE for superior surface lubricity with scratch and abrasion resistance

Features and Benefits

- Convenient, ready-to-use, pourable nonionic wax dispersion
- Synergistic wax combination that enhances PTFE mobility to the coating surface
- PTFE dramatically enhances abrasion resistance
- High density polyethylene provides improved surface slip
- Extra fine particle size provides excellent gloss retention and film clarity

Dry Wax ID

Polyfluo 523XF

Recommended Addition Levels

2.0-5.0% (on total formula weight)

Systems and Applications

Water based coatings. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); interior and exterior can and container coatings.

Typical Properties*

Microspersion 52	3
------------------	---

Wax Solids 40%

Viscosity @ **25** ° C (cP) 1,000 - 2,000

pH 9.5 - 10.5

Density @ 25 ° C (g/cc) 1.03

Wax Mean Particle Size (μ m) 3.5 - 5.5

NPIRI Grind 1.0 - 2.5

PTFE (PFAS) free alternatives: Microspersion 611AL-50, Microspersion 1226XF-50

Apr-25

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com