Micro **Powders**

TECHNICAL DATA

NatureTex[®] Series

Micronized naturally derived cellulose acetate for reducing gloss and adding consistent surface texture and structure to a wide variety of paints and coatings

Features and Benefits

- Provides gloss reduction with improved burnish resistance vs. silica
- Adds mild to moderate texture effects to the coating surface
- Naturally derived and biodegradable in both freshwater and marine environments
- High melting point
- Hydroxyl functionality (OH value 116)
- Microplastic alternative

Composition

Cellulose acetate

Renewable Carbon Index

61%

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based, solvent based, industrial coatings including metal, plastics and masonry, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	NatureTex 325	NatureTex 270	NatureTex 200	NatureTex 140
Decomposition °C	> 230	> 230	> 230	> 230
Density @ 25 $^{\circ}$ C (g/cc)	1.30	1.30	1.30	1.30
Maximum Particle Size (μm)	44 (325 mesh)	53 (270 mesh)	74 (200 mesh)	105 (140 mesh)
Mean Particle Size (µm)	10.0 - 15.0	18.5 - 23.0	35.0 - 45.0	45.0 - 55.0
Moisture Content	<5	<5%	<5%	<5%

FORMULATION ADVISORY: NatureTex may begin to discolor at cure temperatures exceeding 180 °C, with thermal degradation beginning above 230 °C. NatureTex may have some solubility in ester, ketone, and glycol *A* ether based formulas

Apr-25

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

The above data reflects typical properties. Please contact Micro Powders for official product specifications. The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.