

Superslip 6515

Economical combination of polyethylene and amide wax that provides scratch and mar resistance with a smooth surface feel

Features and Benefits

- Polyethylene provides scratch and mar resistance
- EBS provides maximum surface lubricity and block resistance without the use of PTFE
- Imparts a smooth surface "feel"

Composition

HDPE/EBS

Recommended Addition Levels

0.5-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and leather); wood coatings and sanding sealers; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings, sanding sealers.

Typical Properties*

	<u>Superslip 6515</u>
Melting Point ° C	139 - 145
Density @ 25 ° C (g/cc)	0.96
NPIRI Grind	2.0 - 3.0
Maximum Particle Size (µm)	22.00
Mean Particle Size (µm)	6.0 - 8.0

Apr-25