

TECHNICAL DATA

Synfluo 171VF

A cost effective combination of micronized synthetic wax and PTFE for surface lubricity and scratch resistance

Features and Benefits

- Synthetic wax provides slip, scratch and rub resistance
- PTFE provides lubricity, abrasion resistance and antiblocking
- Synergistic wax combination that enhances PTFE mobility to the coating surface
- Conforms to (EU) 2019/1021 & Stockholm Convention (POP)

Composition

Synthetic wax/PTFE

Recommended Addition Levels

0.5-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings.

Typical Properties*

	Synfluo 171VF
Melting Point $^\circ$ C	104 - 110
Density @ 25 $^{\circ}$ C (g/cc)	0.96
NPIRI Grind	2.0 - 3.0
Maximum Particle Size (μm)	22.00
Mean Particle Size (µm)	4.0 - 7.0

PTFE (PFAS) free alternatives: MP-28AL, Synslip 3750

Apr-25

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

The above data reflects typical properties. Please contact Micro Powders for official product specifications. The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.